



Savita Oil Technologies Limited

Plot No. 10/2, Kharadpada, P.O. Naroli, Silvassa 396 230 U.T.D. & NH

T: +917574843505 / 7574843521 / 22 Fax: +91 260 265 0182 www.savita.com

SAVSOL | TRANSOL

TECHNICAL DATA SHEET

Product Name Technol 150 BS

SR. NO.	CHARACTERISTICS	TEST METHOD	TYPICAL VALUES
1	APPEARANCE	VISUAL	Bright & Clear
2	COLOUR	ASTM D-1500	L1.5
3	DENSITY AT 29.5 ^o C,g/cc	ASTM D-1298	0.8830
4	K.VISCOSITY AT 40 ^o C, cst	ASTM D-445	489.62
5	K.VISCOSITY AT 100 ^o C, cst	ASTM D-445	31.87
6	VISCOSITY INDEX	ASTM D-2270	96
7	TOTAL ACID NUMBER, mgKOH/gm	ASTM D- 974	0.03
8	POUR POINT ^o C	ASTM D- 97	-6
9	FLASH POINT ^o C, (COC) ^o C	ASTM D-92	298
10	WATER CONTENT, ppm	ASTM D-6304	50